

# DESOPON<sup>®</sup> USF

## Major component

- Compound of fully synthetic fatliquor and special softening agent

## Property

- Strong combination with leather fiber. Leather can withstand high temperature drying after fatliquoring.
- Give crust softness, fullness and comfortable hand feeling. Give grain tightness.
- Excellent light resistance and heat resistance, suitable for light color leather.
- Excellent acid and electrolyte resistance.

## Specification

Appearance (25 °C) :	Soft paste
Color:	Milky white
Active matter%:	55.0±2.0
pH (10.0% aqueous solution, 25 °C) :	5.0±1.0
Ionicity:	Anionic
Short chain chlorinated paraffin:	Comply with EU REACH laws and regulations
APEO	Comply with EU REACH laws and regulations

## Application

- Recommended main fatliquor formulation for cowhide nappa shoe upper (in terms of shaved wet blue):

<b>DESOPON USF</b>	4.0%
DESOPON SO	3.0%
DESOPON QL	2.0%
DESOPON DPF	3.0%

- Recommended main fatliquor formulation for cowhide upholstery (in terms of shaved wet

This information is based on our current level of knowledge and experience. We do not make any promise or guarantee.

Before use, the customer is still necessary to test the product in order to determine whether it is suitable for the objective production conditions and demand.

# DESOPON® USF

blue):

<b>DESOPON USF</b>	6.0%
DESOPON DPF	4.0%
DESOPON QL	3.0%
DESOPON SO	3.0%

- Recommended main fatliquor formulation for sheepskin garment (in terms of shaved wet blue):

<b>DESOPON USF</b>	5.0%
DESOPON SO	3.0%
DESOPON QL	3.0%
DESOPON DPF	4.0%

## Safety

- This is not a hazardous chemical.
- Observe all the precautions required for handling chemicals.
- Read attentively and observe all the recommendations in our **Material Safety Data Sheet**.

## Transportation and Storage

- The product has a shelf life of at least one year if it is stored in its tightly sealed original packaging at temperatures between 5°C and 35°C.
- The product should be stored in a cool and dry place, lidded and keep upright. Avoid direct exposure to the sun or rain or humidity.
- Appearance may change during storage, if lamination occur, stir well before use, properties will not be affected.
- Re-seal the package immediately after using, use up as soon as possible once the package is opened.
- Read attentively and observe all the recommendations in our **Material Safety Data Sheet**.

---

This information is based on our current level of knowledge and experience. We do not make any promise or guarantee.

Before use, the customer is still necessary to test the product in order to determine whether it is suitable for the objective production conditions and demand.