DESOADDI® AS53M

Major component

• Mixture of polymer binder, fillers, auxiliaries.

Property

• Directly used for roller, and give a good covering ability.
• The film is tight and elastic, with low viscosity and good fluidity.
• Excellent anti-sagging, bending resistance.
• Excellent resistance to cut through on embossing.
• Suitable for all kinds of heavy damaged hides.

Specification

Appearance(25°C):	White or little yellow viscous liquid
Solid Content, %:	36.0±1.0
pH(10.0% aqueous solution, 25°C):	8.0±1.5
Ionicity:	Anionic

Application

• Apply it on the damaged hides by roller.
• 5% pigment can be added when it was applied on dyed leathers.
• The leather should be hung up for about 4 hours after being dealt with this product. And polishing it with 400# sandpaper will be better.

Safety

• This is not a hazardous chemical.
• Observe all the precautions required for handling chemicals.
• Read attentively and observe all the recommendations in our **Safety Data Sheet**.

The information contained in this manual is not a unilateral commitment by our company or a contractual provision. Users are responsible for confirming product suitability under actual conditions.

DESOADDI® AS53M

Transportation and Storage

- The product has a shelf life of one year if it is stored in its tightly sealed original packaging at temperatures between 5°C and 35°C.
- The product should be stored in a cool and dry place, lidded and keep upright. Avoid direct exposure to the sun or frost.
- This product may be stratified with by slight yellowing during storage, and the application effect will not be affected if using it after mixing evenly.
- Re-seal the package immediately after using, use up as soon as possible once the package is opened.
- Read attentively and observe all the recommendations in our **Safety Data Sheet**.

The information contained in this manual is not a unilateral commitment by our company or a contractual provision. Users are responsible for confirming product suitability under actual conditions.